vertisol

HATCHING



MANUFACTURED IN THE EU, REACH COMPLIANT



COLD-CUT, CRUSH-CUT OR ULTRASONIC

| TECHNICAL PROPERTIES Fabric Characteristic | Standard | |
|---|--|--|
| | Standard | 0E 0/ DVC - 1E 0/ DEC |
| Composition | | 85 % PVC + 15 % PES |
| Weight (g/m²) | | 586 ± 5 % |
| Thickness (mm) | | 0.81 ± 5 % |
| Openness factor % | Internal method | 10 % |
| Light fastness | EN ISO 105 B06-2002 (interior)(grey scale level) | 4 White, Other colours 5 |
| Light fastness | EN ISO 105 B02:2002 (interior)(blue scale level) | 7 White, Other colours 8 |
| Tearing resistance (daN) | EN ISO 13937-3:2001 | Warp: 11.6 Weft: 7.3 |
| Breaking strength (daN/5cm) | EN ISO 13934-1:1999 | Warp: 170 Weft: 131 |
| Stretch (%) | EN ISO 13934-1:1999 | Warp: 19 % Weft: 23 % |
| Recycled content | | 2 % Pre-consumer |
| Antibacterial activity | ASTM 2180-18 | Microorganism growth inhibition |
| Roll size | | Width 250 cm, Length 16 m |
| Approximate rapport | | Width direction 47 cm, length direction 0 cm |
| Manufacturing properties | Always store rolls horizontally Cold-cut, crush-cut or ultrasonic Welding: Thermo or ultrasonic Manufacturing direction: | |
| Maintenance | Periodic maintenance: remove dust with vacuum cleaner, dry cloth or compressed air In case of accumulated dirt, it can be cleaned using a sponge or soft brush dipped in soapy water or spray cleaner. In both cases the fabric should be rinsed, leaving the curtain to dry open. Under no circumstances should solvents or abrasives that could damage the fabric coating be used, so care should be taken to avoid paint, varnish or ink stains | |

| Range of colours 2022 | | |
|-----------------------|--|--|
| Petrol | | |
| White | | |
| Ochre | | |
| Slate | | |
| Pine | | |
| Brick | | |



Roller and Vertical blinds (1)

(1) Every Vertical Blind have different aspect because the size of the design. This differences occur and are no ground for claims. This will not be considered as a fault

(2)

All specifications are based on average values and may deviate. The values are given for guidance and are not contractual. Subject to technical modifications



VERTISOL INT'L SRL C-17, KM 18.92 08403 Granollers SPAIN T: + 34 93 840 1444





ISO 9001:2015 and ISO 14001:2015 certified company

www.vertisol.com