vertisol

SKYLINE 2015



VISUAL CONTACT OUTSIDE



COLD-CUT, CRUSH-CUT OR ULTRASONIC



FLAME RETARDANT





TREVIRA CS



MANUFACTURED IN THE EU



ACOUSTIC ABSORPTION



INDOOR AIR QUALITY CERTIFIED

TECHNICAL PROPERTIES						
Fabric Characteristic	Standard					
Composition	-	100 % PES Trevira				
Weight (g/ m²)		178 ± 5 %				
Thickness (mm)		0.31 ± 5 %				
Fire reaction	NF P 92-503 NFPA 701	M-1 Pass				
Light fastness	ISO 105 B02:2002 (blue scale level)	≥5-6				
Openness factor		4 %				
Roll size		240 cm Width 46 m Length				








SUN CONTROL PROPERTIES															
	THERMAL FACTORS						OPTICAL FACTORS								
	Fabric Fabric+Glazing														
	% T _s	% R _s	G _{TOT} in Glazin _§		G _{TOT} in Glazin _i		% T _v	% R _v	% t _{au,n-n}	% t _{au,n-diff}	% T _{uv}	Glare Control	Night Privacy	Visual Contact	Daylight Utilisation
Colour			G _{TOT}	Class	G _{TOT}	Class						Class	Class	Class	Class
Avenida Gray	33	41	0.44	1	0.27	2	32	43	2	30	3	0	2	0	2
Calle Gray	38	33	0.47	1	0.28	2	24	22	3	21	13	0	2	0	2
Ebony	24	24	0.50	0	0.29	2	3	4	2	1	3	3	2	2	1
Kaina Blue	25	31	0.47	1	0.28	2	15	20	3	12	5	1	2	1	2
Linen	42	47	0.42	1	0.27	2	40	49	3	37	19	0	2	0	3
Marina Gray	26	26	0.49	1	0.29	2	6	8	3	3	5	3	2	2	1
Pebble	38	32	0.47	1	0.28	2	25	22	3	22	13	0	2	0	2
Plaza gray	27	44	0.43	1	0.27	2	23	43	9	14	3	0	1	2	2
Rambla Gray	21	28	0.48	1	0.29	2	8	13	2	6	3	2	2	1	1
White	49	36	0.43	1	0.27	2	48	47	3	45	32	0	2	0	4

Data measured according to EN 410:2011 and EN 14500:2021 Calculations of $g_{\mbox{\tiny 100}}$ are according to EN 52022–1 Classification of thermal and visual characteristics according to EN 14501:2021 Data of $g_{\mbox{\tiny 100}}$ are given using standard Glazing C and D.

	Standard	
Acoustic Absorption	EN ISO 10534:2 Measured with 150 mm air chamber	α _w = 0.40* NRC = 0.42**

* Calculated according to EN ISO 11654 ** Calculated according to ASTM C-423.



& health properties

Environmental SKYLINE is Oeko-tex standard 100 certified

Manufacturing properties

Always store rolls horizontally Cold-cut, crush-cut or ultrasonic

Avoid using components or inappropriate packing of the manufactured blind that may cause marks on the

fabric

Manufacturing direction: Blinds can be manufactured 'drop to length' or railroaded. BUT do not place blinds manufactured in different directions in the same área, as this difference

will be spotted

Manufacture panel blinds only 'drop to length'

Maintenance

Vacuum clean for regular maintenance

Do not wash Do not rub Do not steam Do not dry clean









All specifications are based on average values and may deviate. The values are given for guidance and are not contractual. Subject to technical modifications

vertisol

VERTISOL INT'L SRL C-17, KM 18.92 08403 Granollers SPAIN T: + 34 93 840 1444 www.vertisol.com





ISO 9001:2015 and ISO 14001:2015 certified company